

Plant-Mediated Synthesis of Silver Nanoparticles – A Critical Review

Sneha Thakur^{1*}, Krishna Mohan G², Sandhya Rani M²

¹Bojjam Narasimhulu Pharmacy College For Women, Vinay nagar, Saidabad, Hyderabad.

²Center for pharmaceutical sciences, Institute of Science and Technology, JNTU, Kukatapally, Hyderabad.

Received 11th May, 17; Revised 22nd June, 17, Accepted 12th July, 17; Available Online 25th July, 2017

ABSTRACT

Nanomedicine is a revolutionary science nanoparticles of size 1 - 100nm designed for the utilization in disease diagnostics and therapeutics, targeted drug delivery of drugs which have difficulty in solubility and bioavailability and also to be applied in numerous fields. The present critical review aims at enumerating the advantages, synthesis and characterization methods, as well as diversified applications of green silver nanoparticles. Silver nanoparticles is an attractive proposition due to their distinctive physical, chemical and biological properties including a high electrical as well as thermal conductivity, surface-enhanced Raman scattering, chemical stability, catalytic activity and non linear optical behavior which enables them of potential value in inks, microelectronics, and medical imaging. Plant mediated synthesis of silver nanoparticles (AgNPs) is now-a-day's gaining enormous interest as it is cost effective, ecofriendly and has less side effects since there is no addition of external stabilizing or capping agents as the plant itself acts as stabilizing or capping agent. The secondary metabolites and other plant products like proteins, metabolites like alkaloids, terpenoids, saponins, glycosides etc are known to act as external stabilizing or capping agents. The plant mediated silver nanoparticles are known to show uniform particles characteristics and morphology. The bottom to top end approach of synthesis is effective to achieve desired particles size, shape and morphology. The synthesized green silver nanoparticles are characterized by UV-Vis spectroscopy, SEM/TEM analysis, EDAX/EDS, FTIR and other methods zeta potential measurement, thermo gravimetric analysis, Raman scattering. The plant mediated synthesized silver nanoparticles (green silver nanoparticles) are effective in delivering pharmacological activities like antimicrobial, anticancer, larvicidal etc. Also green Silver nanoparticles have diverse applications acting as biosensors, as targeted drug delivery candidates, in diagnostics and therapeutics, in medical and consumer products, as anti pollutant and in agriculture. The future perspective holds promising results in green synthesis of silver nanoparticles involving plants. This review projects a collective sequence of information for synthesizing and evaluation of green silver nanoparticles and scope of its pharmacological actions.

Keywords: Silver nanoparticles, AgNPs, UV-Vis, SEM/TEM, EDAX/EDS, FTIR.

INTRODUCTION

Nanomedicine is a revolutionary science involving nanoparticles of dimensions ranging between 1 - 100nm are designed for the utilization in disease diagnostics for identifying pathology of disease with sensitivity, provide therapy at molecular level with greater degree of cell specificity and targeted drug delivery of drugs which have difficulty in solubility and bioavailability. Nanotechnology is extensively being applied to provide targeted drug therapy, diagnostics, tissue regeneration, cell culture, biosensors and other tools in the field of molecular biology¹. During the past few years, researchers have gained enormous interest in developing the silver nanoparticles (AgNPs) due to their distinctive physical, chemical and biological properties including a high electrical as well as thermal conductivity, surface-enhanced Raman scattering, chemical stability, catalytic activity and non linear optical behavior which enables them of potential value in inks, microelectronics, and medical imaging. Ag-NPs also exhibited broad spectrum bactericidal and fungicidal Activity with extraordinary defense against wide range of microorganisms and also

due to the appearance of drug resistance against commonly used antibiotics. This property increased the commercial value of products in areas of plastics, soaps, pastes, food and textiles. The use of Nanosilver technologies has appeared in a variety of manufacturing processes and end products. The principle behind the use is to store the silver ions in the moisture layer released enabling them to act against bacterial/fungal pathogens². The silver nanoparticles are monitored for various physico-chemical parameters and green synthesis of the silver nanoparticles is safe and effective way to combat harmful effects of synthetic chemicals³. The distinct physico-chemical characteristics of AgNPs have made them applicable in various fields like biomedical⁴, targeted drug delivery⁵, water treatment⁶, agricultural etc.⁷. AgNPs are also applied in inks, adhesives, electronic devices, pastes etc. due to high conductivity⁸. AgNPs have been synthesized by physio-chemical techniques such as chemical reduction⁸, gamma ray radiation⁹, micro emulsion¹⁰, electrochemical method¹¹, laser ablation¹², autoclave¹³, microwave¹⁴ and photochemical reduction¹⁵. These methods have effective yield, but they are associated with the limitations like use




Figure 1: Synthesis of plant mediated silver nanoparticles.

of toxic chemicals and high operational cost and energy needs. These physico-chemical methods though have effective yield are prone to limitations like use of toxic chemicals, high operational cost and energy needs. Hence cost-effective and energy efficient new alternative for AgNPs synthesis using natural polymers¹⁵, plant extracts¹⁶, animals, and microorganisms¹⁷ as reducing and capping agents are now popular strategies. The synthesis assembly of silver nanoparticles using plants has got critical attention due to its rapid, ecofriendly, non-pathogenic, economical advantage and providing a single step technique for the biosynthetic processes. The silver ions are acted upon by stabilizing and capping agents of combination of secondary metabolites and other biomolecules such as proteins, amino acids, enzymes, polysaccharides, alkaloids, tannins, phenolics, saponins, terpenoids and vitamins which are chemically diverse in nature possessing medicinal values and are environmental benign¹⁹. The green synthesis of nanoparticles will unfold new areas of targeted therapeutics, diagnosis and conventional use²⁰.

The present review describes the systemic description of green synthesis of nanoparticles from plants,

characterization techniques and multiple facets of applications of silver nanoparticles.

Green synthesis of nanoparticles

The green synthesis of the silver nanoparticles involves the interaction of reducing biological material with the aqueous silver nitrate solution. The temperature and other conditions have to be monitored during the reaction. The biological material itself acts as the stabilizing and capping agent, hence no external stabilizers or capping agents are required in green synthesis when compared to conventional chemical methods where toxic chemicals are used as stabilizers and capping agents. The commonly used biological agents are plants, micro organisms, biopolymers and animals. The literature supports wide use of plants, micro organisms, biopolymers as biological agents and very few reports of animal sources. The plant parts like leaves, bark, root, flower, fruits, seeds etc are used in the synthesis. The microbial cell mass of both intracellular and extracellular nature is involved in the synthesis of AgNPs. The biopolymers like collagen and chitosan are widely used.

The nanoparticles prepared from the plants have well defined surface characteristics like size, shape and morphology. The solvent used in most of the cases is water

also other solvents like ethyl acetate, methanol and ethanol²²⁻²⁶. The phytochemicals like secondary metabolites, chlorophyll²² and proteins²³ of the plant are responsible to act as reducing and stabilizing agents. The green synthesis of AgNPs using the plant as biological agent is mentioned in Fig 1. Many plants with effective activities were utilized as sources for the synthesis of AgNPs. The synthesized AgNPs from the following plants, their shape and size along with their pharmacological screening are reported in Table.1 were found to have appropriate particle size shape and morphology. The synthesized AgNPs are separated as pellet or powders using ultracentrifugation or also dried³.

The synthesis involves the reaction of the aqueous silver nitrate solution in which the Ag⁺ ion has 1mm concentration (widely used by researchers) with the biological reducing agents involving extracts of plants as shown in Fig. no.1. No external stabilizing and capping agents are added generally. The major physical and chemical factors that affect the AgNPs synthesis are reaction temperature, metal ion concentration, extract contents, pH of the reaction mixture, duration of reaction and agitation. Parameters like metal ion concentration, extract composition and reaction period largely affect the size, shape and morphology of the AgNPs. The suitable conditions for synthesis of AgNPs include basic pH, 25-37 °C temperature and controlled agitation³. However in few cases the external chemical agents like sodium-dodecyl sulphate were used for stabilization the AgNPs²¹.

Characterization of silver nanoparticles

The common characterization techniques used are UV- Vis spectroscopy, SEM, TEM, FTIR, XRD, EDAX/EDS analysis as shown in Table.1. Also analysis of zeta potential, thermal stability by thermo gravimetric analysis, circular dichroism study and concentration and conversion of AgNPs by inductive couple plasma is studied.

UV- Vis spectroscopy- The change in the color from colorless to light yellow is indicative of nanoparticles formation by many researchers and the SPR peak is generally observed at significant range of 400 - 450 nm characteristic for AgNPs⁴². The UV-Vis spectral analyses is used to analyze the dependency of pH, metal ion concentration, extract content on the formation of AgNPs and reveal the size-stability of synthesized AgNPs by exhibiting red shift in the SPR peak with increase in size of nanoparticles and blue shift for decrease in size⁴³.

SEM / TEM analysis- The SEM/TEM analysis is used to determine the shape of the AgNPs. Many of the plants revealed different shapes and structures of nanoparticles like cubic²⁷, irregular³⁶, spherical³⁹, hexagonal⁴⁴, polyhedral⁴⁵, isotropic⁴⁴, flake⁴⁶, flower⁴⁷, pentagonal⁴⁸, anisotropic⁴⁹ and rod like structures⁵⁰.

Dynamic light scattering (DLS) – The DLS is used for the measurement of average hydrodynamic parameters along with poly dispersive indexes.

FTIR analysis- FTIR analysis determines the interaction of the capping agents to achieve efficient stabilization.

X-ray diffraction analysis- XRD analysis is used to determine the lattice structure (morphology) of the synthesized nanoparticles like FCC (face centered cube),

bcc (body centered cube) etc., The XRD studies of almost all the researchers reported the formation of face centered cubic (FCC) crystalline structured for AgNPs.

Energy dispersive spectroscopy EDAX/EDS-, EDS analyses the elemental composition in the nanomaterials, which is exhibited at a characteristic optical absorption band peak around 3 KeV with silver weight percentage ranging from 45% to 80%. The reported stability of synthesized AgNPs has varied from 1 day to 1 year depending upon reducing agents and other operating conditions^{51,52}.

Raman scattering - Raman spectroscopy detects the vibrational modes of molecules and can be used to identify vibrational signals of a variety of chemical species that are attached to the surface of nanoparticles during synthesis giving an idea about the surface morphology of the nanoparticles⁵³.

Pharmacological applications

Antimicrobial activity

The antigenic capacity of the microorganisms against current antibiotics projects always a need for production of new antibiotics that possess broad spectrum activity. Silver has been used since years as a effective antimicrobial agent against a wide range of over 650 microorganisms from different classes such as gram-negative and gram-positive bacteria, fungi or viruses. Silver is known to interact with the disulphide bonds of the glycoprotein/ protein contents of microorganisms such as viruses, bacteria and fungi resulting in change of three dimensional structures of proteins thus blocking the functional operations of the microorganism. The silver ions may also form reactive oxygen species which interacts and damages the ATP assembly of respiration. Both silver nanoparticles and silver ions may also accumulate inside the cells of microbes causing damage to cell and thus are effective as antimicrobial agents possibly due to this mechanism^{54, 55}. The antimicrobial action may be summarized as shown in the Fig.2.

Antibacterial property

Bacterial cell lysis could be one of reason for its antibacterial property; the possible mechanism of the silver ions involves interaction of silver molecules with biological macromolecules such as enzymes and DNA through an electron-release mechanism or free radical production. The silver may bind to thiol groups (ASH) of enzymes to form stable SAAg bonds thus deactivating enzymes in the cell membrane that involve in trans membrane energy generation and ion transport. Also Ag(I) ions intercalates between the purine and pyrimidine base pairs disrupting the hydrogen bonding between the two anti-parallel strands and denaturing the DNA molecule. Gram-positive bacteria are less susceptible to Ag+ than gram-negative bacteria due to more peptidoglycan cell wall (negatively charged) than gram-negative bacteria, as silver ions are positively charged; more silver may get stuck by peptidoglycan in gram-positive bacteria than in gram-negative bacteria⁵⁶. Few plants have been reported to have antibacterial activity as reported in Table 1 like *Solanum tricobactum*³⁶, *Syzygium cumini*³⁶, *Centella asiatica*³⁶, *Citrus sinensis*³⁶, *Vitis vinifera*⁴⁰ etc.




Figure 2: antimicrobial action of AgNPs.

Table 1: Plant mediated synthesis and elucidation of some plants along with pharmacological evaluation.

S no	Plant material	Spectroscopic analysis	Size, Shape and morphology	Conditions of operation	Activity studied
1.	Aqueous extract of <i>Alternanthera sessilis</i> ²⁷	UV-Vis TEM XRD FTIR	<100nm in size with crystalline nature		Quick reducing agent for silver ions and significant anti proliferative effect against prostate cancer cells
2.	Aqueous <i>Aloe</i> leaf extract ²⁸	UV-Vis TEM XRD	20 nm in size with spherical shape and FCC Structure	0.1 - 1.5 mM, 20 min, 20°C - 40°C, 0 to 15 ml/1 ml, Hydrazine hydrate content: 1- 15 ml, Static	Antibacterial to <i>E. coli</i> and <i>S. aureus</i>
3.	Aqueous extract of <i>Boerhaavia diffusa</i> plant powder ²⁹	UV-Vis FTIR SEM EDAX XRD TEM	25 nm in size with spherical shape and FCC, Cubic structure	0.1 mM, 24 hr, 100°C, 10 ml/90 ml, Stirred	Antibacterial to fish pathogens <i>A. hydrophilia</i> , <i>F.branchiophilum</i> , <i>P.fluorescens</i>
4.	Filtered aqueous Mesocarp extract of <i>Cocos nucifera</i> ³⁰	UV-Vis TEM XRD	24 nm in size, spherical shape and FCC structure	1 mM, 1 hr, 60°C, 20 ml/80 ml, Stirring, pH—2 - 11	Larvicidal nature
5.	Filtered aqueous extract of <i>Delphinium denudatum</i> root powder ³¹	UV-Vis FTIR FESEM XRD	<85 nm Size, spherical Shape and FCC Structure	1 mM, 2hr, room temp. 1.5 ml/30 ml, Static, 20 min at 12000 rpm	Anti-bacterial against <i>S. aureus</i> , <i>B. cereus</i> , <i>E. coli</i> and <i>P. aeruginos</i> Larvicidal to <i>Aedes aegypti</i>
6.	Methanol extract and essential oil of <i>Eucalyptus leucoxylon</i> leaf ³²	UV-Vis SEM TEM XRD	50 nm in Size, Spherical Shape and FCC Structure	120 min, room temp. static	AgNP with biomedical potential

7.	Ethanollic extracts of <i>Phytolacca decandra</i> , <i>Gelsemium sempervirens</i> , <i>Hydrastis canadensis</i> and <i>Thuja occidentalis</i> ³³	UV Vis SEM EDAX FTIR	90-130nm in size, spherical shape and crystalline nature	300 K temperature, 10 min time	beneficial biological action
8.	<i>Indigofera aspalathoides</i> , aqueous leaf extracts ³⁴	UV Vis SEM EDAX FTIR	20 – 50 nm in Size		Water-soluble organics leaf extract responsible to reduction. Wound healing applications
9.	<i>Morinda citrifolia</i> root extract ³⁵	UV-Vis SEM TEM XRD	30-55 nm in size, spherical shape, crystalline in nature		cytotoxic effect on HeLa cell
10.	Filtered ethanollic extracts of <i>Solanum tricobactum</i> , <i>Syzygium cumini</i> , <i>Centella asiatica</i> and <i>Citrus sinensis</i> plant powders ³⁶	UV Vis SEM EDAX FTIR	41 - 53 nm in size, irregular Shape and FCC Structure	1 mM, 24 - 48 hr, 37°C, 10 ml/5 ml, Additive: ammonium solution= 2.5 ml, agitated	Antibacterial against pathogenic <i>P. aeruginosa</i>
11.	Filtered aqueous extract of <i>Mangifera indica</i> linn peel ³⁷		7 - 27 nm in Size, spherical shape and FCC Structure	0.5 to 4 mM, 15 to 90 min, 25 to 100°C, 0.1 to 3 ml/27 ml, pH: 2 - 11. Static	Stable for 3 months, AgNPs loaded on fabrics exhibited antimicrobial property.
12.	Filtered aqueous extract of <i>Lonicera japonica</i> L leaf ³⁸	UV-Vis FTIR SEM TEM AFM ZP	36 - 72 nm in size, spherical shape	1 to 9 mM, 24 hr, 40°C - 80°C, 5% to 40% (v/v), Static, 5 min at 10000 rpm	Stability: zeta potential— 41mV
13.	Filtered aqueous extract of <i>Terminalia chebula</i> fruit powder ³⁹ .	UV-Vis FTIR HR-TEM XRD EDS DLS	25 nm in size With FCC structure and phyto Capped nature	10 mM, room temp. 1 ml/25 ml, pH: 4 – 9, Static	Stabile for 10 days, AgNps showed catalytic activity on the reduction of methylene blue
14.	<i>Vitis vinifera</i> Extract ⁴⁰	UV-Vis SEM XRD	10 - 880 nm size, spherical shape with FCC, cubic and hexagonal structure	1 mM, 10 hr, room temp. 10 ml/90 ml, Static. 15 min at 2000 rpm	Antibacterial to <i>B. subtilis</i> , <i>E. coli</i> , <i>P. aeruginosa</i> and <i>S. pneumoniae</i>
15.	<i>Withania somnifera</i> Leaf Powder ⁴¹	UV-Vis FTIR TEM XRD EDAX	5 - 30 nm in Size, spherical. Shape and FCC Structure	100 mM, sunlight: 5min, dark room: 12hr, room temp. 100 ml/1 ml, Static	AgNPs with quasi-reversible redox behavior Anti-bacterial to <i>E. coli</i> and <i>S. aureus</i> Anti-fungal to <i>A. niger</i> , <i>A. flavus</i> and <i>C. albicans</i>
16.	<i>Abutilon indicum</i> L. leaf extract ⁶³	UV-Vis FTIR TEM EDAX	10-30 nm size, spherical shape,	2 mM, sunlight: 5min, dark room: 24hr, room temp	dose dependent free radical scavenging activity and anticancer activity against MCF-7 breast cancer cell line.

Antifungal activity

AgNPs are much effective fast-acting fungicides against a broad spectrum of common fungi including such as *Aspergillus*, *Candida* and *Saccharomyces*⁵⁷. Silver nanoparticles of *Withania somnifera* was found to exhibit

antifungal activity against *A. niger*, *A. flavus* and *C. albicans*⁴¹.

Larvicidal activity

Due to the gaining population of vector borne diseases, the new type of larvicides is in demand. The AgNPs are known

to show the larvicidal activity by killing the larvae of vectors at early stage. Many AgNPs have shown larvicidal activity against malarial vectors *Aedes aegypti*³¹, *A. subpictus*³¹, and filariasis vector *Culex quinquefasciatus*⁵⁹ and other parasites^{31,60} of plants like *Cocos nucifera*³⁰ *Delphinium denudatum*³¹ *Hibiscus rosasinensis*⁵. No attempt has been made to elucidate a possible mechanisms of larvicidal activities has been made.

Wound Healing Activity

During apoptosis, the mitochondria are activated in the cell to reduce its viability. The AgNPs are found to show wound healing activity by penetrating into the fibroblast cells and accumulating over time but do not interfere with the cell viability. The

AgNPs were found to show wound healing potential by reducing the mitochondrial activity⁶¹. *Indigofera aspalathoides* mediated AgNPs were tested for wound-healing applications following excision in animal models³⁴. *Arnebia nobilis* root extract was found to have wound healing activity in an excision animal model exerting a positive effect due to their antimicrobial potential and provided a novel therapeutic direction for wound treatment in clinical practice⁶².

Anti cancer activity

The need for potent anticancer agents is always a topic of interest. The potential targets need for effective therapy with less side effects is matter of concern. Green silver nanoparticles are cost effective, ecofriendly and have less side effects when compared to conventional chemotherapy, and synthetic drugs. The silver nanoparticles were found to have antiproliferative, cytotoxic activities. Silver nanoparticles synthesized using *Acalypha indica* Linn show only 40% cell inhibition against human breast cancer cells (MDA-MB-231)⁶⁴. The differences in their level of anticancer activity against A375 skin melanoma cells was observed for the AgNPs synthesized using the ethanolic extracts of *Phytolacca decandra*, *Gelsemium sempervirens*, *Hydrastis canadensis*, and *Thuja occidentalis* showed beneficial biological action³³. The cell death (100%) of the HeLa cell line was observed with 100 µg of AgNPs synthesized using the root of *Morinda citrifolia*³⁵. The piperidine, piperlongumine, and piperlonguminine present in *Piper longum* may be responsible for the synthesis of silver nanoparticles and exhibited a significant cytotoxic effect (94.02%) at 500 µg/mL on HEp-2 cell lines⁶⁵. The aqueous extract of *Alternanthera sessilis*²⁷ was quick reducing agent for silver ions and was found to have significant anti proliferative effect against prostate cancer cells.

Miscellaneous applications

These nanoparticles have been used in a diverse range of applications such as biosensors⁶⁶, targeted drug delivery candidates⁶⁷, diagnostics and therapeutic agents⁶⁸, cancer treatments⁶⁹, pesticides⁷⁰, and antimicrobials⁷¹, water treatment⁷², anti fouling agents⁷³. Medical and consumer products

Water treatment

Stable AgNPs synthesized using *Anacardium occidentale* fresh leaf extract at 80°C bud as a novel probe for sensing chromium ions [Cr⁺⁶] in tap water.

Anti fouling agents⁷³

The AgNPs may be used to treat many environmental concerns like; air disinfection, water disinfection, ground water and biological water disinfection and surface disinfection.

Medicinal Textiles and Devices- Extract of *Curcuma longa* tuber powder capped silver nanoparticles exhibited minimum bactericidal concentration for *Escherichia coli* BL-21 strain at 50mg/L. The immobilization onto the cotton cloth using sterile water is reported to show better bactericidal activity when compared to polyvinylidene fluoride immobilized cloth⁷⁴. The incorporation of *Azadirachta indica* synthesized silver nanoparticles into cotton cloth results in antibacterial effect against *E. coli*⁷⁵.

Catalytic activity

Filtered aqueous extract of *Terminalia chebula* fruit powder³⁹ showed catalytic activity on the reduction of methylene blue. Extract of *Acacia nilotica* pod mediated AgNPs modified glassy carbon electrode showed greater catalytic activity on the reduction of benzyl chloride compared to those of glassy carbon and metallic Ag electrode⁷⁶.

Agriculture

Emerging application of Ag nanoparticles particularly is in crop protection and the management of agricultural plant diseases^{77,78}.

CONCLUSION

The present review focuses on plant mediated synthesis of silver nanoparticles and its advantages with multi-access of its applications- an emerging area of nanotechnology. There is a steady increase in the publication scenario regarding the current topic. The angiosperm species has been widely used in comparison with the other sources of plants like gymnosperms, ferns etc. There are several characterizations methods for confirmation and simplest bottom to top approach of synthesis is advantageous due to its cost effectiveness, ecofriendly nature and fewer side effects as there is no additional stabilizing or capping agent added in plant mediated synthesis. The AgNPs synthesized using biological reducing and capping agents have shown wide variation in shape and size. The synthesized plant mediated silver nanoparticles have diverse applications like the anti-microbial action, anticancer activity, larvicidal activity, wound healing activity. Also plant mediated silver nanoparticles were found to have miscellaneous applications in fields of diagnostics and therapeutics, medicinal and consumer products, targeted drug delivery areas, agriculture and as ecofriendly. The results, however, are conflicting and there is a need for more focus to resolve new arenas in this field. The potential of AgNPs for their use as drug carriers in cancer therapy, as biosensors for metabolites and pollutants, as catalyst etc. is quite high and requires intensive and integrated research activity for harnessing it. Finally, we hope that this critical review may help scientists, researchers, and teachers in the field of materials science and nanotechnology.

CONFLICT OF INTERESTS

The authors declare that there is no conflict of interests regarding the publication of this paper.

ACKNOWLEDGMENT

The authors thank the Jawaharlal Nehru Technological University, Kukatpally, Hyderabad, for providing research facilities.

REFERENCES

1. Surendiran, A., Sandhiya, S., Pradhan, S.C & Adithan, C, Novel applications of nanotechnology in medicine, *Indian J Med Res* 130, December 2009, pp 689-701.
2. Quang Huy Tran, Van Quy Nguyen and Anh-Tuan Le, Silver nanoparticles: synthesis, properties, toxicology, applications and perspectives, *Adv. Nat. Sci.: Nanosci. Nanotechnol.* 4 (2013) 033001(20pp) doi:10.1088/2043-6262/4/3/033001.
3. Srikar, S.K., Giri, D.D., Pal, D.B., Mishra, P.K. and Upadhyay, S.N. Green Synthesis of Silver Nanoparticles: A Review. *Green and Sustainable Chemistry*, 2016, 6, 34-56. <http://dx.doi.org/10.4236/gsc.2016.61004>.
4. Chaloupka, K., Malam, Y. and Seifalian, A.M. Nanosilver as a New Generation of Nanoproduct in Biomedical Applications. *Trends in Bioethanology*, 2010, 28, 580-588.
5. Prow, T.W., Grice, J.E., Lin, L.L., Faye, R., Butler, M., Becker, W., Wurm, E.M.T., Yoong, C., Robertson, T.A., Soyer, H.P. and Roberts, M.S. Nanoparticles and Microparticles for Skin Drug Delivery. *Advanced Drug Delivery Reviews*, 2011, 63, 470-491. <http://dx.doi.org/10.1016/j.addr.2011.01.012>.
6. Dankovich, T.A. and Gray, D.G. (2011) Bactericidal Paper Impregnated with Silver Nanoparticles for Point-of-Use Water Treatment. *Environmental Science & Technology*, 45, 1992-1998. <http://dx.doi.org/10.1021/es103302t>.
7. Nair, R., Varghese, S.H., Nair, B.G., Maekawa, T., Yoshida, Y. and Sakthi Kumar, D. Nanoparticulate Material Delivery to Plants. *Plant Science*, 2010, 179, 154-163. <http://dx.doi.org/10.1016/j.plantsci.2010.04.012>.
8. Khan, Z., Al-Thabaiti, S.A., Obaid, A.Y. and Al-Youbi, A.O. Preparation and Characterization of Silver Nanoparticles by Chemical Reduction Method. *Colloids and Surfaces B: Biointerfaces*, 2011, 82, 513-517. <http://dx.doi.org/10.1016/j.colsurfb.2010.10.008>.
9. Chen, P., Song, L.Y. and Liu, Y.K. Synthesis of Silver Nanoparticles by Gamma-Ray Irradiation in Acetic Water Solution Containing Chitosan. *Radiation Physics and Chemistry*, 2007, 76, 1165-1168. <http://dx.doi.org/10.1016/j.radphyschem.2006.11.012>.
10. Zhang, W.Z., Qiao, X.L. and Chen, J.G. Synthesis and Characterization of Silver Nanoparticles in AOT Micro- Emulsion System. *Chemical Physics*, 2006, 300, 495-500. <http://dx.doi.org/10.1016/j.chemphys.2006.09.029>.
11. Reicha, F.M., Sarhan, A., Abdel-Hamid, M.I. and El-Sherbiny, I.M. Preparation of Silver Nanoparticles in the Presence of Chitosan by Electrochemical Method. *Carbohydrate Polymers*, 2012, 89, 236-244. <http://dx.doi.org/10.1016/j.carbpol.2012.03.002>.
12. Abid, J.P., Wark, A.W., Brevetm, P.F. and Girault, H.H. Preparation of Silver Nanoparticles in Solution from a Silver Salt by Laser Irradiation. *Chemical Communications*, 2002, 7, 792-793. <http://dx.doi.org/10.1039/b200272h>.
13. Yang, J. and Pan, J. Hydrothermal Synthesis of Silver Nanoparticles by Sodium Alginate and Their Applications in Surface-Enhanced Raman Scattering and Catalysis. *Acta Materialia*, 2012, 60, 4753-4758. <http://dx.doi.org/10.1016/j.actamat.2012.05.037>.
14. Khan, A., El-Toni, A.M., Alrokayan, S., Alsalhi, M., Alhoshan, M. and Aldwayyan, A.S. (2011) Microwave-Assisted Synthesis of Silver Nanoparticles Using Poly-N Isopropyl Acrylamide/Acrylic Acid Microgel Particles. *Colloids and Surfaces A: Physicochemical and Engineering Aspects*, 377, 356-360. <http://dx.doi.org/10.1016/j.colsurfa.2011.01.042>.
15. Alarcon, E.I., Udekwo, K., Skog, M., Pacioni, N.L., Stamplecoskie, K.G., González-Béjar, M., et al. The Biocompatibility and Antibacterial Properties of Collagen-Stabilized, Photochemically Prepared Silver Nanoparticles. *Biomaterials*. 2012, 33, 4947-4956. <http://dx.doi.org/10.1016/j.biomaterials.2012.03.033>.
16. Song, J.Y. and Kim, B.S. Rapid Biological Synthesis of Silver Nanoparticles Using Plant Leaf Extracts. *Bioprocess and Biosystems Engineering*, 2009, 32, 79-84. <http://dx.doi.org/10.1007/s00449-008-0224-6>.
17. Sharma, V.K., Yngard, R.A. and Lin, Y. Silver Nanoparticles: Green Synthesis and Their Antimicrobial Activities. *Advances in Colloid and Interface Science*, 2009, 145, 83-96. <http://dx.doi.org/10.1016/j.cis.2008.09.002>.
18. Huang, H. and Yang, X. Synthesis of Polysaccharide-Stabilized Gold and Silver Nanoparticles: A Green Method. *Carbohydrate Research*, 2004, 339, 2627-2631. <http://dx.doi.org/10.1016/j.carres.2004.08.005>.
19. Shakeel Ahmed, Mudasir Ahmad, Babu Lal Swami, Saiqa Ikram, A review on plants extract mediated synthesis of silver nanoparticles for antimicrobial applications: A green expertise, *Journal of Advanced Research*. 2016, 7, 17-28. <http://dx.doi.org/10.1016/j.jare.2015.02.007>.
20. Philip, D. Honey Mediated Green Synthesis of Silver Nanoparticles. *Spectrochimica Acta Part A: Molecular and Biomolecular Spectroscopy*, 2010, 75, 1078-1081. <http://dx.doi.org/10.1016/j.saa.2009.12.058>.
21. Rao, P., Chandraprasad, M.S., Lakshmi, Y.N., Rao, J., Aishwarya, P. and Shetty, S. Biosynthesis of Silver Nanoparticles Using Lemon Extract and Its Antibacterial Activity. *International Journal of Multidisciplinary and Current Research*. 2014, 2, 165-169.
22. Shafaghat, A. Synthesis and Characterization of Silver Nanoparticles by Photosynthesis Method and Their Biological Activity. *Synthesis and Reactivity in Inorganic, Metal-Organic, and Nano-Metal Chemistry*. 2014, 45, 381-387. <http://dx.doi.org/10.1080/15533174.2013.819900>.

23. Kulkarni, A.P., Srivastava, A.A., Nagalgaon, R.K. and Zunjarrao, R.S. Phytofabrication of Silver Nanoparticles from a Novel Plant Source and Its Application. *International Journal of Biological & Pharmaceutical Research*. 2012, 3, 417-421.
24. Logeswari, P., Silambarasan, J. and Abraham, J. Synthesis of Silver Nanoparticles Using Plants Extract and Analysis of Their Antimicrobial Property. *Journal of Saudi Chemical Society*. 2015, 19, 311-317. <http://dx.doi.org/10.1016/j.jscs.2012.04.007>.
25. Rajesh, S., Raja, D.P., Rathi, J.M. and Sahayaraj, K. Biosynthesis of Silver Nanoparticles Using *Ulva fasciata* (Delile) Ethyl Acetate Extract and Its Activity against *Xanthomonas campestris* pv. *Malvacearum*. *Journal of BiopestiS. Cides*. 2012, 5, 119-128.
26. Bankar, A., Joshi, B., Kumar, A.R. and Zinjarde, S. Banana Peel Extract Mediated, Novel Route or the Synthesis of Silver Nanoparticles. *Colloids and Surfaces A: Physicochemical and Engineering Aspects*. 2010, 368, 58-63. <http://dx.doi.org/10.1016/j.colsurfa.2010.07.024>.
27. Firdhouse. M. J and Lalitha. P, "Biosynthesis of silver nanoparticles using the extract of *Alternanthera sessilis* —antiproliferative effect against prostate cancer cells. *Cancer Nanotechnology*. 2013, vol. 4, no. 6, pp. 137–143.
28. Zhang, Y., Cheng, X., Zhang, Y., Xue, X. and Fu, Y. Biosynthesis of Silver Nanoparticles at Room Temperature Using Aqueous *Aloe Leaf* Extract and Antibacterial Properties. *Colloids and Surfaces A: Physicochemical and Engineering Aspects*. 2013, 423, 63-68. <http://dx.doi.org/10.1016/j.colsurfa.2013.01.059>.
29. Vijaykumar, P.P.N., Pammi, S.V.N., Kollu, P., Satyanarayana, K.V.V. and Shameem, U. () Green Synthesis and Characterization of Silver Nanoparticles Using *Boerhaavia diffusa* Plant Extract and Their Antibacterial Activity. *Industrial Crops and Products*. 2014, 52, 562-566. <http://dx.doi.org/10.1016/j.indcrop.2013.10.050>.
30. Roopan, S.M., Rohit, Madhumitha, G., Rahuman, A.A., Kamraj, C., Bharathi, A. and Surendra, T.V. Low-Cost and Eco-Friendly Phyto-Synthesis of Silver Nanoparticles Using *Cocos nucifera* Coir Extract and Its Larvicidal Activity. *Industrial Crops and Products*. 2013, 43, 631-635. <http://dx.doi.org/10.1016/j.indcrop.2012.08.013>.
31. Suresh, P., Gunasekar, P.H., Kokila, D., Prabhu, D., Dinesh, D., Ravichandran, N., Ramesh, B., Koodalingam, A. and Siva, G.V. Green Synthesis of Silver Nanoparticles Using *Delphinium denundatum* Root Extract Exhibits Antibacterial and Mosquito Larvicidal Activities. *Spectrochimica Acta Part A: Molecular and Biomolecular Spectroscopy*. 2014, 127, 61-66. <http://dx.doi.org/10.1016/j.saa.2014.02.030>.
32. Rahimi-Nasrabadi, M., Pourmortazavi, S.M., Shandiz, S.A.S., Ahmadi, F. and Batooli, H. Green Synthesis of Silver Nanoparticles Using *Eucalyptus leucoxylon* Leaves Extract and Evaluating the Antioxidant Activities of the Extract. *Natural Product Research*. 2014, 28, 1964-1969. <http://dx.doi.org/10.1080/14786419.2014.918124>.
33. Das S., Das J., Samadder A., Bhattacharyya S. S, Das, D. and Khuda-Bukhsh A. R., "Biosynthesized silver nanoparticles by ethanolic extracts of *Phytolacca decandra*, *Gelsemium sempervirens*, *Hydrastis canadensis* and *Thuja occidentalis* induce differential cytotoxicity through G2/M arrest in A375 cells. *Colloids and Surfaces B: Biointerfaces*. 2013, vol. 101, pp. 325–336.
34. Arunachalam, K.D., Annamalai, S.K., Arunachalam, A.M. and Kennedy, S. Green Synthesis of Crystalline Silver Nanoparticles Using *Indigofera Aspalathoides*-Medicinal Plant Extract for Wound Healing Applications. *Asian Journal of Chemistry*, 2013, 25, S311-S314.
35. Suman TY, Radhika Rajasree SR, Kanchana A, Elizabeth SB, "Biosynthesis, characterization and cytotoxic effect of plant mediated silver nanoparticles using *Morinda citrifolia* root extract. *Colloids and Surfaces B: Biointerfaces*, 2013, vol. 106, pp. 74–78.
36. Logeswari, P., Silambarasan, S. and Abraham, J. Ecofriendly Synthesis of Silver Nanoparticles from Commercially Available Plant Powders and Their Antibacterial Properties. *Scientia Iranica*, 2013, 20, 1049-1054.
37. Yang, N. and Li, W.H. *Mango Peel Extract* Mediated Novel Route or Synthesis of Silver Nanoparticles and Antibacterial Application of Silver Nanoparticles Loaded onto Non-Woven Fibers. *Industrial Crops and Products*, 2013, 48, 81-88. <http://dx.doi.org/10.1016/j.indcrop.2013.04.001>.
38. Kumar, V. and Yadav, S.K. Synthesis of Stable, Polyshaped Silver and Gold Nanoparticles Using Leaf Extract of *Lonicera japonica* L. *International Journal of Green Nanotechnology*, 2011, 3, 281-291. <http://dx.doi.org/10.1080/19430892.2011.633474>.
39. Edison, T.J.I. and Sethuraman, M.G. Instant Green Synthesis of Silver Nanoparticles Using *Terminalia chebula* Fruit Extract and Evaluation of Their Catalytic Activity on Reduction of Methylene Blue. *Process Biochemistry*, 2012, 47, 1351-1357. <http://dx.doi.org/10.1016/j.procbio.2012.04.025>.
40. Chaudhary, S., Paul, S. and Sagar, S. Biosynthesis of Silver Nanoparticles Using *Vitis vinifera* Extract and Evaluation of Their Antimicrobial Activity. *International Journal of Bio-Technology and Research*. 2012, 2, 1-12.
41. Raut, R.W., Mendhulkar, V.D. and Kashid, S.B. Photosensitized Synthesis of Silver Nanoparticles Using *Withania somnifera* Leaf Powder and Silver Nitrate. *Journal of Photochemistry and Photobiology B: Biology*. 2014, 132, 45-55. <http://dx.doi.org/10.1016/j.jphotobiol.2014.02.001>.
42. Sastry, M., Mayyaa, K.S. and Bandyopadhyay, K. pH Dependent Changes in the Optical Properties of Carboxylic Acid Derivatized Silver Colloid Particles. *Colloids and Surfaces A: Physicochemical and Engineering Aspects*, 1997, 127, 221-228. [http://dx.doi.org/10.1016/S0927-7757\(97\)00087-3](http://dx.doi.org/10.1016/S0927-7757(97)00087-3).

43. Poinern, G.E.J.; Shah, M.; Chapman, P.; Fawcett, D. Green biosynthesis of silver nanocubes using the leaf extracts from *Eucalyptus macrocarpa*. *Nano Bull.* 2013, 2, 1–7.
44. Vigneswaran, N., Ashtaputre, N.M., Varadarajan, P.V., Nachane, R.P., Paralikar, K.M. and Balasubramanya, R.H. Biological Synthesis of Silver Nanoparticles Using the Fungus *Aspergillus flavus*. *Materials Letters.* 2007, 61, 1413–1418. <http://dx.doi.org/10.1016/j.matlet.2006.07.042>.
45. Ortega-Arroyo, L., Martin-Martinez, E.S., Aguilar-Mendez, M.A., Cruz-Orea, A., Hernandez-Perez, I. and Glorieux, C. Green Synthesis Method of Silver Nanoparticles Using Starch as Capping Agent Applied the Methodology of Surface Response. *Starch/Starke.* 2013, 65, 814–821. <http://dx.doi.org/10.1002/star.201200255>.
46. Kaviya, S., Santhanalakshmi, J. and Viswanathan, B. Biosynthesis of Silver Nanoflakes by *Crossandra infundibuliformi* Leaf Extract. *Materials Letters.* 2012, 67, 64–66. <http://dx.doi.org/10.1016/j.matlet.2011.09.023>.
47. Sreekanth, T.V.M., Nagajyothi, P.C. and Lee, K.D. (*Dioscorea Batatas* Rhizome-Assisted Rapid Biogenic Synthesis of Silver and Gold Nanoparticles. Synthesis and Reactivity in Inorganic, Metal-Organic, and Nano-Metal Chemistry. 2012, 42, 567–572. <http://dx.doi.org/10.1080/15533174.2011.613886>.
48. Raja kumar, G. and Rahuman, A.A. Larvaidal Activity of Synthesized Silver Nanoparticles Using *Eclipta prostrate* Leaf Extract against Filariasis and Malaria Vectors. *Acta Tropica.* 2011, 118, 196–203. <http://dx.doi.org/10.1016/j.actatropica.2011.03.003>.
49. Sant, D.G., Gujarathi, T.R., Harne, S.R., Ghosh, S., Kitture, R., Kale, S., Chopade, B.A. and Pardesi, K.R. *Adiantum phillipense* L. Frond Assisted Rapid Green Synthesis of Gold and Silver Nanoparticles. *Journal of Nanoparticles*, 2013, Article ID: 182320.
50. Satishkumar, G., Gobinath, G., Karpagam, K., Hemamalini, V., Premkumar, K. and Sivaramakrishna, S. Phyto- Synthesis of Silver Nanoscale Particles Using *Morinda citrifolia* L. and Its Inhibitory Action against Human Pathogens. *Colloids and Surfaces B: Biointerfaces.* 2012, 95, 235–240. <http://dx.doi.org/10.1016/j.colsurfb.2012.03.001>.
51. Klug, H.P.; Alexander, L.E. X-ray Diffraction Procedures for Poly-crystallite and Amorphous Materials, 1974 2nd ed.; Wiley: New York, NY, USA.
52. Barrett, C.S.; Cohen, J.B.; Faber, J.; Jenkins, R.; Leyden, D.E.; Russ, J.C.; Predecki, P.K. *Advances in X-ray Analysis*; Plenum Press: New York, NY, USA, 1986; Volume 29.
53. Kneipp, K.; Wang, Y.; Kneipp, H.; Perelman, L.T.; Itzkan, I.; Dasari, R.R.; Fela, M.S. Single molecule detection using surface-enhanced Raman scattering (SERS). *Phys. Rev. Lett.* 1997, 78, 1667–1670. [CrossRef].
54. Sadeghi B, Gholamhoseinpoor F. A study on the stability and green synthesis of silver nanoparticles using *Ziziphora tenuior* (Zt) extract at room temperature. *Spectrochim Acta Part A: Mol Biomol Spectrosc* 2015;134:310–5.
55. Rai M, Yadav A, Gade A. Silver nanoparticles as a new generation of antimicrobials. *Biotechnol Adv* 2009; 27:76–83.
56. Ankanna S, Prasad TNVKV, Elumalai EK, Savithramma N. Production of biogenic silver nanoparticles using *Boswellia valifoliolata* stem bark. *Dig J Nanomater Biostruct* 2010; 5:369–72.
57. Yu H, Chen M, Rice PM, Wang SX, White RL, Sun S. Dumbbell-like bifunctional Au-Fe₃O₄ nanoparticles. *Nano Lett* 2005;5(2):379–82.
58. Sareen Sarah J., Pillai Raji K, Chandramohanakumar N and Balagopalan M, Larvicidal Potential of Biologically Synthesised Silver Nanoparticles against *Aedes Albopictus*, *Research Journal of Recent Sciences*, 2012, Vol. 1(ISC-2011), 52-56, ISSN 2277-2502.
59. Mondal, N.K., Chaudhury, A., Mukhopadhyaya, P., Chatterjee, S., Das, K. and Datta, J.K. , Green Synthesis of Silver Nanoparticles and Its Application for Mosquito Control. *Asian Pacific Journal of Tropical Disease.* 2014, 4, S204-S210. [http://dx.doi.org/10.1016/s2222-1808\(14\)60440-0](http://dx.doi.org/10.1016/s2222-1808(14)60440-0).
60. Marimuthu, S., Rahuman, A.A., Rajakumar, G., Santhoshkumar, T., Kirthi, A.V., Jayaseelan, C., Bagavan, A., Zahir, A.A., Elango, G. and Kamaraj, C. Evaluation of Green Synthesized Silver Nanoparticles against Parasites. *Parasitology Research.* 2011, 108, 1541–1549. <http://dx.doi.org/10.1007/s00436-010-2212-4>.
61. Chiara Rigo , Letizia Ferroni, Ilaria Tocco, Marco Roman , Ivan Munivrana , Chiara Gardin , Warren Cairns R. L. , Vincenzo Vindigni , Bruno Azzena , Carlo Barbante 4 and Barbara Zavan, Active Silver Nanoparticles for Wound Healing, *Int. J. Mol. Sci.* 2013, 14, 4817–4840; doi:10.3390/ijms14034817.
62. Garg .S, Chandra.A, Mazumder .A, and Mazumder .R, Green synthesis of silver nanoparticles using *Arnebia nobilis* root extract and wound healing potential of its hydrogel, *Asian Journal of Pharmaceutics*, 2014; vol. 8, no. 2, pp. 95–101.
63. Ramesh B and Rajeshwari R. et al. / *Asian Journal of Phytomedicine and Clinical Research.* 2015, 3(4), 124 - 131.
64. C. Krishnaraj, P. Muthukumar, R. Ramachandran, M. Balakumar, and P. Kalaichelvan, “*Acalypha indica* Linn: biogenic synthesis of silver and gold nanoparticles and their cytotoxic effects against MDA-MB-231, human breast cancer cells,” *Biotechnology Reports*, 2014, vol. 4, pp. 42–49.
65. Justin Packia Jacob S., Finub J. S., and Narayanan A., “Synthesis of silver nanoparticles using *Piper longum* leaf extracts and its cytotoxic activity against Hep-2 cell line,” *Colloids and Surfaces B: Biointerfaces*, vol. 91, no. 1, pp. 212–214, 2012.
66. Doria, G.; Conde, J.; Veigas, B.; Giestas, L.; Almeida, C.; Assunção, M.; Rosa, J.; Baptista, P.V. Nobel metal nanoparticles for biosensing applications. *Sensors* 2012, 12, 1657–1687. [CrossRef] [PubMed].

67. Le, X.; Poinern, G.E.J.; Subramaniam, S.; Fawcett, D. Applications of nanometre scale particles as pharmaceutical delivery vehicles in medicine. *Open J. Biomed. Mater. Res.* 2015, 2, 11–26.
68. Youns, M.; Hoheisel, J.D.; Efferth, T. Therapeutic and diagnostic applications of nanoparticles. *Curr. Drug Targets* 2011, 12, 357–365. [CrossRef] [PubMed].
69. Fortina, P.; Kricka, L.J.; Graves, D.J.; Park, J.; Hyslop, T.; Tam, F.; Halas, N.; Surrey, S.; Waldman, S.A. Applications of nanoparticles to diagnostics and therapeutics in colorectal cancer. *Trends Biotechnol.* 2007, 145–152. [CrossRef] [PubMed].
70. Al-Samarrai, A.M. Nanoparticles as alternative to pesticides in management plant diseases—A Review. *Int. J. Sci. Res. Publ.* 2012, 2, 1–4.
71. Rai, M.; Yadav, A.; Gade, A. Silver nanoparticles as a new generation of antimicrobials. *Biotechnol. Adv.* 2009, 27, 76–83. [CrossRef] [PubMed].
72. Balavigneswaran .C. K., Kumar T. S. J., Packiaraj R. M., and Prakash S., Rapid detection of Cr(VI) by AgNPs probe produced by *Anacardium occidentale* fresh leaf extracts, *Applied Nanoscience*, 2014, vol. 4, no. 3, pp. 367–378.
73. Tran, Q.H., Nguyen, V.Q. and Le, A.T. (2013) Silver Nanoparticles: Synthesis, Properties, Toxicology, Applications and Perspectives. *Advances in Natural Sciences: Nanoscience and Nanotechnology*, 4, Article ID: 033001. <http://dx.doi.org/10.1088/2043-6262/4/3/033001>.
74. Sathishkumar .M, Sneha .K, and Yun. Y.-S, “Immobilization of silver nanoparticles synthesized using *Curcuma longa* tuber powder and extract on cotton cloth for bactericidal activity,” *Bioresource Technology*, 2010, vol. 101, no. 20, pp. 7958–7965.
75. Tripathi. A, Chandrasekaran .N, Raichur .A.M, and Mukherjee .A., Antibacterial applications of silver nanoparticles synthesized by aqueous extract of *Azadirachta Indica* (Neem) leaves, *Journal of Biomedical Nanotechnology*, 2009, vol. 5, no. 1, pp. 93–98.
76. Jebakumar .T.N, Immanuel Edison and Sethuraman .M. G., Electrocatalytic reduction of benzyl chloride by green synthesized silver nanoparticles using pod extract of *Acacia nilotica*,” *ACS Sustainable Chemistry and Engineering*, 2013, vol. 1, no. 10, pp.1326–1332.