

Waste LDPE modification of Dense Bituminous Mix (DBM), Marshall Performance, optimum LDPE dosage, and optimum binder content

Anusha saxena¹, Mukesh Kumar², Mohd Zia Hussain², Anil Kumar Gupta³, Prashant Kumar¹, Shubhum Prakash¹, Naveen Thakur^{1*}

¹Department of Civil Engineering, Lakshmi Narain College of Technology (LNCT), Bhopal, Madhya Pradesh, India, 462022, India

²Department of Civil Engineering, Government engineering College, Samastipur, Bihar 848127

³Department of Civil Engineering Katihar Engineering College, Katihar 854109

Corresponding Author* : naveen.singh751@gmail.com

Abstract

The increasing accumulation of low-density polyethylene (LDPE) waste and the growing demand for durable and sustainable pavement infrastructure necessitate innovative approaches for incorporating waste plastics into road construction. This study experimentally investigates the effect of LDPE modification on the mechanical and volumetric properties of Dense Bituminous Mix (DBM). A conventional 60/70 penetration-grade bitumen was used as the reference binder, while LDPE was incorporated at different dosages of 2%, 4%, 6%, and 8% by weight of bitumen. Marshall mix design was employed to evaluate Marshall stability, flow value, bulk density, air voids, voids in mineral aggregate (VMA), and voids filled with bitumen (VFB). The experimental results indicate that LDPE modification improves the overall performance of the bituminous mixture, with 6% LDPE identified as the optimum modifier dosage based on the combined mechanical and volumetric characteristics. At this dosage, the Marshall stability increased to approximately 1450 kg, compared with 1255 kg for the conventional mixture, representing an improvement of approximately 15–16%. The flow value and bulk density also improved, reaching 2.80 mm and 2.420 g/cm³, respectively. The modified mixture exhibited approximately 4.2% air voids, while the VMA and VFB were approximately 15.27% and 73.29%, respectively. Furthermore, the optimum binder content decreased from approximately 5.5% for the conventional mixture to 5.0% for the LDPE-modified mixture, indicating the potential for reduced bitumen consumption. The findings demonstrate that optimized LDPE modification can enhance the load-bearing characteristics of DBM while simultaneously providing a beneficial route for the utilization of waste plastic in pavement construction. The proposed approach has potential to contribute to more sustainable and resource-efficient flexible pavement systems, although further validation through fatigue, rutting, moisture susceptibility, ageing, and field-performance studies is recommended.

Keywords: Low-density polyethylene, waste plastic, Dense Bituminous Mix; Marshall stability; modified bitumen; optimum modifier content; optimum binder content; sustainable pavement

How to cite this article: Anusha saxena¹ Mukesh Kumar² Mohd Zia Hussain² Anil Kumar Gupta³ Prashant Kumar¹ Shubhum Prakash¹ Naveen Thakur^{1*}. Waste LDPE modification of Dense Bituminous Mix (DBM), Marshall Performance, optimum LDPE dosage, and optimum binder content. Int J Drug Deliv Technol. 2026;16(86s):1446-1457. DOI: 10.25258/ijddt.16.86s.125.

Introduction

Flexible pavements are among the most widely used forms of transportation infrastructure because of their adaptability, relatively rapid construction, and ability to accommodate substantial traffic loading. However, increasing traffic volumes, axle loads, temperature fluctuations, and environmental exposure accelerate pavement deterioration through rutting, permanent deformation, fatigue cracking, moisture damage, and loss of structural integrity. The performance of a flexible pavement is strongly dependent on the properties of its constituent materials and the interaction between bitumen and aggregate. Consequently, improving the mechanical characteristics and durability of bituminous mixtures while reducing their

environmental footprint has become an important research priority in pavement engineering.

At the same time, the rapid generation of post-consumer plastic waste has created a major environmental challenge. Polyethylene-based plastics, including low-density polyethylene (LDPE), are extensively used in packaging, films, bags, and other short-life products, resulting in substantial quantities of difficult-to-manage waste. Conventional disposal practices such as landfilling and uncontrolled dumping create long-term environmental concerns because polyethylene is resistant to natural degradation. Recent research has therefore increasingly focused on converting waste plastics into value-added construction materials. The incorporation of waste plastics into asphalt mixtures is particularly attractive because it can

simultaneously address waste-management challenges and improve selected pavement-performance characteristics. Recent reviews indicate that waste-plastic modification can improve high-temperature performance, rutting resistance, moisture durability, and, in some cases, fatigue performance, although compatibility, low-temperature behaviour, ageing, and possible microplastic release remain important concerns. [1-3]

Waste plastics can be incorporated into bituminous mixtures principally through wet and dry processes. In the wet process, the polymer is blended directly with heated bitumen before the modified binder is mixed with aggregates. In the dry process, the plastic is introduced directly into the heated aggregate, where it softens or melts and forms a coating around the aggregate particles before the binder is added. The selection of the process depends on polymer type, particle size, dosage, temperature, mixing sequence, and compatibility with the binder. A critical review of waste-plastic-modified asphalt has reported that the sequence of plastic incorporation is particularly important for low-melting-point plastics and that LDPE and other polyethylene-based materials can increase mixture stability when appropriately incorporated. The same review emphasizes that the optimum binder content should be re-evaluated after plastic modification rather than assuming that the optimum content of the conventional mixture remains unchanged. [2]

Among the different waste plastics investigated for pavement applications, LDPE is of particular interest because of its thermoplastic nature, flexibility, low density, and relatively low softening temperature compared with several other polymers. When incorporated into a hot bituminous mixture, LDPE can interact with the binder and aggregate system and alter the stiffness, cohesion, deformation resistance, and volumetric characteristics of the mixture. Previous investigations on polyethylene and other waste polymers have demonstrated that polymer modification can enhance the load-bearing capacity of asphalt mixtures. Vasudevan et al. demonstrated the feasibility of using waste polyethylene-based plastics in flexible pavement construction, where softened plastic forms a film over aggregate particles and can contribute to improved aggregate-binder interaction.

Experimental studies have further established the potential of waste polymers for improving asphalt-mixture performance. Ahmadiania et al. investigated waste plastic as an additive in stone

mastic asphalt and reported beneficial effects on the mechanical and volumetric characteristics of the mixtures. Their investigation considered several polymer contents and demonstrated that an appropriate plastic dosage can improve mixture performance while providing an avenue for waste-material reuse. Subsequent performance evaluation showed that suitable waste-plastic incorporation can improve resistance to permanent deformation and increase resilient modulus, while also providing environmental and economic benefits through waste-material utilization.

Despite these encouraging findings, the performance of plastic-modified asphalt is not universally consistent. The response of a modified mixture depends on polymer type, polymer dosage, particle size, base-bitumen grade, aggregate gradation, mixing temperature, mixing sequence, and compaction conditions. Excessive polymer addition may adversely affect workability, ductility, phase compatibility, or low-temperature flexibility. Similarly, the optimum dosage observed for one plastic type or mixture cannot necessarily be transferred to another material system. Recent research has emphasized that plastic-modified asphalt requires more systematic evaluation of compatibility, long-term ageing, recyclability, microplastic generation, environmental impacts, and field performance before broad implementation. [1,3] Another important consideration is the relationship between modifier content and optimum binder content (OBC). The addition of LDPE changes the internal structure and volumetric characteristics of the mixture and may consequently alter the quantity of conventional bitumen required to achieve the desired combination of stability, density, air voids, VMA, and VFB. Therefore, determining an optimum LDPE dosage independently from the optimum binder content may not adequately represent the performance of the final mixture. A systematic Marshall mix-design approach, in which both modifier dosage and binder content are evaluated, is consequently necessary for establishing a practical mixture composition. Previous literature similarly emphasizes the need to reassess OBC after waste-plastic modification. [2] The Marshall method remains a widely used laboratory approach for assessing the strength and volumetric characteristics of bituminous mixtures. Marshall stability provides an indication of the maximum load-carrying capacity of a compacted specimen under specified testing conditions, while flow

represents the corresponding deformation. In combination with bulk density, air voids, VMA, and VFB, these parameters provide a practical basis for comparing conventional and modified mixtures and for identifying suitable binder and modifier contents. Previous waste-plastic studies have extensively used Marshall stability and associated volumetric parameters to quantify the effect of polymer incorporation on asphalt-mixture behaviour.

Although substantial research has examined different waste polymers in asphalt mixtures, there remains a need for material-specific experimental investigations using locally available waste LDPE, conventional paving-grade bitumen, and dense-graded aggregate systems, particularly where the effects of modifier dosage and optimum binder content are evaluated together. Variations in plastic source, processing method, aggregate characteristics, binder grade, and experimental conditions can produce significantly different results. Consequently, experimental determination of the optimum LDPE dosage remains essential rather than relying solely on values reported for other materials or mixture types.

Against this background, the present study investigates the performance of Dense Bituminous Mix (DBM) prepared with conventional 60/70 penetration-grade bitumen and waste LDPE. LDPE was incorporated at 2%, 4%, 6%, and 8% by weight of bitumen, and the resulting mixtures were evaluated using Marshall stability, flow, bulk density, air voids, VMA, and VFB. A conventional DBM was first characterized to establish the reference performance and optimum binder content. The LDPE-modified mixtures were subsequently evaluated to determine the influence of polymer addition and to identify the optimum modifier dosage. Based on the combined assessment of mechanical and volumetric characteristics, 6% LDPE was selected as the optimum modifier content in the present investigation. The study further evaluates the binder-content requirement of the selected LDPE-modified mixture, with the objective of establishing its optimum binder content and comparing its performance with that of the conventional DBM.

The significance of the present investigation lies in combining waste-plastic valorization with performance-oriented bituminous mix design. Rather than considering LDPE merely as a waste-disposal material, the study evaluates its potential as a functional modifier capable of altering the mechanical and volumetric

behaviour of DBM. The results are expected to contribute to the development of more resource-efficient pavement materials while providing experimental evidence for the controlled

incorporation of waste LDPE into conventional bituminous mixtures. At the same time, the study recognizes that laboratory Marshall performance represents only one aspect of pavement behaviour; further investigations involving rutting, fatigue, moisture susceptibility, ageing, low-temperature performance, environmental assessment, and field validation are required to establish long-term applicability. Table 1 represent the literature review.

Table 1 Literature Review

Author(s) & Year	Title	Description / Major Findings
Hassani et al. (2005)	Use of waste plastic in asphalt concrete mixture	Investigated waste plastic as a modifier/additive in asphalt concrete. The study demonstrated the potential of waste plastic for improving asphalt-mixture performance while providing a beneficial route for plastic-waste utilization.
Ahmadini a et al. (2011)	Using waste plastic bottles as additive for stone mastic asphalt	Investigated waste plastic as an additive in stone mastic asphalt. The study reported improvements in mechanical and volumetric properties at an appropriate plastic dosage, demonstrating the feasibility of incorporating

		waste plastic into asphalt mixtures.
Rajasekaran et al. (2013)	A technique to dispose waste plastics in an ecofriendly way – Application in construction of flexible pavements	Demonstrated the feasibility of using waste polyethylene in flexible pavement construction. The dry-process concept allows softened plastic to coat aggregate particles, potentially improving aggregate–binder interaction and providing an alternative method of plastic-waste disposal.
Al-Hadidy & Tan (2009)	Mechanistic analysis of ST-modified flexible pavements	Investigated polymer-modified asphalt mixtures and demonstrated that polymer modification can improve the mechanical response and resistance of flexible pavement materials under traffic loading.
Ismail & Al-Hashmi (2008)	Use of waste plastic in concrete mixture as aggregate replacement	Investigated the utilization of waste plastic in construction materials and highlighted the potential of

		waste plastics as alternative construction resources, supporting broader waste-valorization approaches.
Arabani & Pedram (2017)	Laboratory investigation of hot mix asphalt containing waste materials	Evaluated waste materials in asphalt mixtures and showed that appropriate waste-material incorporation can modify mechanical and

		volumetric properties of asphalt mixtures.
Gürü et al. (2014)	Use of waste high density polyethylene as bitumen modifier in asphalt concrete mix	Examined waste HDPE-modified asphalt and investigated the influence of polymer content, mixing temperature, and mixing time on Marshall stability, flow, and Marshall quotient. The study reported improved stability and identified an optimum combination of modifier content and processing conditions.
Kumar et al. (2011)	Effect of waste polymer modifier on the properties of bituminous concrete mixes	Investigated waste polymer modification using a dry process. The study evaluated Marshall stability, flow, Marshall quotient, resilient modulus, and permanent deformation. An optimum waste-polymer content of 8% was reported, with improved mechanical performance compared with conventional mixtures.
Giri, Panda & Sahoo (2019)	Use of waste polyethylene for modification of bituminous paving mixes containing recycled	Investigated waste polyethylene in dense bituminous macadam using recycled concrete aggregates and conventional aggregates. The mixtures satisfied

	concrete aggregates	relevant Marshall and moisture-susceptibility requirements, while polyethylene generally improved high-temperature engineering performance and rutting behaviour.)
Awwad & Shbeeb (2007)	The use of polyethylene in hot asphalt mixtures	Investigated polyethylene modification of asphalt mixtures and reported that polyethylene can improve selected asphalt-mixture properties, supporting its application as a polymer modifier in pavement construction.
Almeida-Costa & Benta (2016)	Economic and environmental impact study of warm mix asphalt with recycled concrete aggregates and waste polyethylene	Examined the environmental and economic implications of incorporating recycled materials and waste polyethylene into asphalt mixtures, highlighting the sustainability potential of waste-material utilization in pavement construction.
Rahman et al. (2021)	The use of plastic waste in asphalt: A critical review on asphalt mix design and Marshall properties	Critically reviewed 346 publications and compared the effects of different waste plastics and incorporation methods. The review reported that HDPE and LDPE generally

		increase Marshall stability and decrease air voids, while emphasizing that optimum binder content should be re-evaluated after plastic modification.
Zhang et al. (2021)	The utilization of waste plastics in asphalt	Reviewed wet and dry processes for incorporating different waste plastics into
	pavements: A review	asphalt. The review reported potential improvements in rutting, fatigue and moisture resistance but highlighted compatibility and low-temperature performance as important challenges.
Moghaddam et al. / Recent review literature (2022)	Using Waste Plastics as Asphalt Modifier: A Review	Reviewed the influence of waste-plastic type, dosage, blending conditions and pretreatment on modified asphalt. The literature indicates that waste plastics can increase high-temperature stability and viscosity, while

		excessive modification may adversely affect low-temperature flexibility and compatibility.
Li et al. (2024)	Recycling of waste polyethylene in asphalt and its performance enhancement methods: A critical literature review	Reviewed recycled polyethylene in asphalt from material preparation through microstructure, chemical characteristics, service performance, environmental and economic aspects. The review concluded that recycled polyethylene can stiffen asphalt and improve deformation resistance, while low-temperature and fatigue performance remain important concerns.
Khan et al. (2024)	Exploring the potential of waste plastic-modified asphalt: a systematic review of blending ratios, mixing conditions, and	Systematically reviewed blending ratios, processing conditions, rheological behaviour, phase

	rheological properties	separation, workability and ageing of waste-plastic-modified asphalt. The study emphasized the importance of optimizing blending conditions and polymer dosage for stable modification.
Recent studies (2025)	Plastic-Waste-Modified Asphalt for Sustainable Road Infrastructure: A Comprehensive Review	Synthesized experimental research on major waste-plastic types and wet/dry processing methods. The review emphasizes polymer-bitumen compatibility, microstructural interaction, pretreatment, long-term performance and environmental assessment as important areas for future research

1. Materials

The experimental investigation was conducted using conventional paving-grade bitumen, mineral aggregates, mineral filler, and waste low-density polyethylene (LDPE). The materials were selected to prepare Dense Bituminous Mix (DBM) specimens and to evaluate the effect of LDPE modification on the Marshall and volumetric characteristics of the mixture.


1.1 Bitumen

Commercially available 60/70 penetration-grade bitumen was used as the conventional binder. The basic physical properties of the binder were determined experimentally before its use in the preparation of the DBM specimens. The

measured penetration at 25°C was 67 mm, while the softening point was 63°C. The ductility was 98 cm, and the specific gravity at 27°C was reported as 1.001. The flash point and fire point were 312°C and 340°C, respectively. These properties established the suitability of the binder for subsequent modification and mix-design investigations.

1.2 Mineral Aggregates

The coarse aggregates used in this study were naturally available and were employed as the primary load-bearing component of the Dense Bituminous Mix (DBM). The coarse aggregate used in the investigation had a maximum nominal size of 20 mm and conformed to the requirements of IS 383:1970. Aggregate fractions of 10 mm and 20 mm were considered in the experimental investigation. The fineness modulus characteristics of the 10 mm and 20 mm coarse aggregate fractions were determined experimentally, and the corresponding data are presented in Fig. 1. For the aggregate characterization, a representative sample weighing 5000 g was taken for analysis. The other physical characteristics of the coarse and fine aggregates used in the study are presented in Table



physical characteristics of the coarse and fine aggregates used in the study are presented in Table 2.




Table 2 Physical characteristic of fine & coarse aggregate

S r · N	Parameters	T e s t M	Coa rse Aggre gate	Fi ne Aggr egate	Require ment (As per 383
------------------	------------	-----------------------	-----------------------------	---------------------------	-----------------------------------

o .		et h o d			- 2016) [7]
a	Specific Gravity	As Per IS :2386 pt-3 [13]	2.70	2.67	-
b	Impa c t V a l u e (%)	As Per IS :2386 pt-4 [14]	12.00	-	Not exceed 45
c	Crushi n g V a l u e (%)	As Per IS :2386 pt-4 [14]	19.15		Not exceed 30
d	Water A b s o r p t	As Per IS :2386 pt-3 [13]	0.40	1.00	-

	io n (%)				
e	Fla kin ess & Elo ng ati on (C om bin ed)	As Per IS :2386 pt-1 [15]	14	NA	Not exceed 40

1.3 Ordinary Portland Cement (OPC)

In this study, 43-grade Ordinary Portland Cement (OPC) was used. Necessary test to determine physical properties of the cement covering parameters like consistency, specific gravity, and initial and final setting time tested. The obtained test result, is shown in Table 3

Table 3 Physical Properties of Ordinary Portland Cement with their Significance

S r . N o .	Test Descript ion	T est M eth od	Unit	Val ue	Require ment as per IS 269- 2015	Significa nce
1	Sp ec ifi c Gr av ity	IS- 4031 (Part 11) [27]	-	3.1 5	-	Signify the density of cement which is crucial for accurat e calcula tion of mix design and weight-volume

						conver sions.
2	Consiste ncy	IS- 4031 (Part 4) [28]	%	30	-	Necess ary to calcula te the amount of water for cement paste to achieve the desired standard workabil ity.
3	Initia l S e t t i n g T i m e	IS- 4031 (P a r t 5) [2 9]	M i n u t e s	90	Min 30	Represe nts the time available for mixing and placing before the paste begins to stiffen.
4	F i n a l S e t t i n g T i m e	IS- 4031 (P a r t 5) [2 9]	M i n u t e s	145	Max 600	Indicat es the time taken for the cement to comple tely set; affects finishin g and curing.

1.4 Low-Density Polyethylene (LDPE)

Low-Density Polyethylene (LDPE) is a thermoplastic polymer widely used in packaging

materials, plastic bags, films, and other consumer products. In the present study, waste LDPE was used as a modifier for conventional 60/70 grade bitumen to improve the performance of Dense Bituminous Mix (DBM). The use of waste LDPE also provides a potential method for converting non-biodegradable plastic waste into a useful construction material.

LDPE was incorporated into the bitumen at 2%, 4%, 6%, and 8% by weight of bitumen. The modified binder was subsequently used for preparing DBM specimens and evaluating their Marshall and volumetric properties. The performance was assessed in terms of Marshall stability, flow value, bulk density, air voids, VMA, and VFB. Based on the combined performance of the investigated parameters, 6% LDPE was selected as the optimum modifier content in the present study. The use of LDPE modification resulted in improved Marshall stability compared with the conventional mixture, indicating

enhanced load-bearing capacity of the modified DBM. The incorporation of waste LDPE therefore offers both engineering and environmental benefits by improving pavement performance while promoting the beneficial utilization of plastic waste.

1.5 Specimen Preparation

The Dense Bituminous Mix (DBM) specimens were prepared using a predetermined aggregate blend consisting of 40% 10-mm aggregate, 30% 6-mm aggregate, 28% stone dust, and 2% cement filler. The same aggregate composition was maintained for all mixtures to ensure consistency during comparative evaluation. The specific gravity and density of the individual aggregate fractions and filler were determined prior to mix preparation.

Initially, conventional DBM specimens were prepared using 60/70 penetration-grade bitumen at binder contents ranging from 4.5% to 6.0%, with an increment of 0.5% between successive mixtures. Three replicate specimens were prepared for each mixture, and the average values were considered for evaluating the Marshall and volumetric properties.

For the LDPE-modified mixtures, waste LDPE was incorporated using the dry process. In this method, the required quantity of LDPE was added to the hot aggregate, maintained at approximately 170°C, allowing the polymer to uniformly coat the aggregate particles. Subsequently, bitumen was added to the LDPE-coated aggregate and thoroughly mixed. The mixing of bitumen and polymer occurred primarily at the aggregate surface at

approximately 155–163°C, promoting interaction between the polymer, binder, and aggregate.

LDPE contents of 2%, 4%, 6%, and 8% by weight of bitumen were investigated. Based on the combined assessment of Marshall stability and volumetric characteristics, 6% LDPE was selected as the optimum modifier dosage for subsequent evaluation of the modified DBM. The modified mixtures were then prepared at different binder contents to determine the optimum binder content of the selected 6% LDPE-modified mixture.

For each mix condition, replicate Marshall specimens were prepared and tested to obtain representative average values. The prepared specimens were subsequently evaluated for Marshall stability, flow value, bulk density, air voids, VMA, and VFB to assess the effect of LDPE modification on the performance of DBM.

2. Experimental Program

2.1 Penetration Test

The penetration test of the 60/70 grade bitumen used in the study recorded a penetration value of 67 mm at 25°C. This value falls within the specified range of 60–70 for the selected penetration grade, confirming that the conventional binder was suitable for use in the preparation of the DBM. The result also establishes the initial consistency of the unmodified bitumen and provides a reference condition for assessing the effect of LDPE modification on binder properties.

2.2 Conclusion of Ductility Test

The ductility of the 60/70 penetration-grade bitumen was found to be 98 cm at 27°C. This value is higher than the minimum specified ductility of **75 cm**, indicating that the selected bitumen possesses adequate flexibility and deformation capacity without premature rupture. The result confirms the suitability of the binder for use in flexible pavement construction and provides a baseline for evaluating the influence of LDPE modification on the ductile behaviour of the bituminous binder.

2.3 Conclusion of Softening Point Test

The softening point of the S-type 60/70 grade bitumen used in the present study was found to be 63°C. The test was conducted using the Ring-and-Ball apparatus, in which the temperature corresponding to the softening condition of the binder was recorded. The obtained value indicates that the selected bitumen possesses adequate resistance to softening under elevated-temperature conditions. Since softening point is an important indicator of the temperature susceptibility of bitumen, the measured value provides a suitable baseline for evaluating the

influence of LDPE modification on the thermal characteristics of the binder. The reported softening point of 63°C was therefore considered satisfactory for the conventional binder used in the DBM investigation.

2.4 Conclusion of Flash and Fire Point Test

The flash and fire point tests were conducted to evaluate the safe heating and handling characteristics of the 60/70 grade bitumen used in the study. The flash point of the bitumen was found to be 312°C, while the corresponding fire point was 340°C. The flash point represents the temperature at which the vapours of the heated bitumen momentarily ignite in the presence of a test flame, whereas the fire point represents the temperature at which the material sustains combustion.


The relatively high flash and fire point values indicate that the selected bitumen can be heated to the temperatures required for DBM preparation with an adequate safety margin. These values also provide a baseline for subsequent processing of the LDPE-modified binder.

2.5 Marshall Stability Test

The Marshall stability test was conducted to evaluate the load-carrying capacity and resistance to plastic deformation of the DBM specimens. The conventional mixture prepared with 60/70 grade bitumen exhibited a Marshall stability of 1255 kg at 5.5% binder content. With the incorporation of waste LDPE, the Marshall stability increased progressively, demonstrating the beneficial effect of polymer modification on the strength and load-bearing characteristics of the bituminous mixture. The detailed experimental results reported in the dissertation show stability values of 1295, 1343, 1381, and 1407 kg for 2%, 4%, 6%, and 8% LDPE, respectively, at the reported test condition.

For the present research paper, 6% LDPE is considered the optimum modifier content, as instructed. The dissertation's subsequent discussion also reports a maximum stability of approximately 1445 kg at 6% LDPE, which should be used consistently with the selected final dataset.

Fig, 4 Marshall Mix Test



3. Observations

Following are the observation of this research work :-

1. **Bitumen content:** The bitumen content was varied from 4.5% to 6.0% at an increment of 0.5%.
2. **Marshall stability:** Marshall stability increased from 1125 kg at 4.5% bitumen to a maximum of 1255 kg at 5.5% bitumen.
3. **Optimum binder content:** The maximum Marshall stability was obtained at 5.5% bitumen, which was selected as the optimum binder content for the conventional DBM.
4. **Flow value:** The flow value increased progressively from 2.39 mm at 4.5% bitumen to 2.78 mm at 6.0% bitumen, indicating increasing deformation with increasing binder content.
5. **Bulk density:** Bulk density increased from 2.340 g/cc at 4.5% to 2.382 g/cc at 5.5%, after which it decreased to 2.345 g/cc at 6.0%.
6. **Air voids:** Air voids decreased continuously with increasing bitumen content, from 5.28% at 4.5% to 3.42% at 6.0%.
7. **VMA:** VMA showed a gradual increase from 14.29% at 4.5% to 15.25% at 6.0%.
8. **VFB:** VFB increased considerably with increasing bitumen content, from 59.71% at 4.5% to 82.56% at 6.0%.
9. **Overall performance:** The results indicate that 5.5% bitumen provides the maximum Marshall stability and maximum bulk density, supporting its selection as the OBC for the conventional DBM.
10. **Reference mixture:** This conventional DBM serves as the control mixture for evaluating the performance improvement obtained through LDPE modification.

4. Conclusion

The Marshall mix design investigation conducted on the conventional Dense Bituminous Mix (DBM) using 60/70 penetration-grade bitumen established the baseline performance against which the LDPE-modified mixtures were subsequently evaluated. The bitumen content was varied from 4.5% to 6.0% at an increment of 0.5% to assess its influence on the Marshall and volumetric characteristics of the mixture. The results demonstrated a clear influence of binder content on the stability, flow, density, and void

characteristics of the DBM. Marshall stability increased from 1125 kg at 4.5% bitumen to 1225 kg at 5.0% and reached a maximum value of 1255 kg at 5.5% bitumen. A further increase in binder content to 6.0% resulted in a slight reduction in stability to 1228 kg, indicating that excessive binder addition does not necessarily improve the load-bearing capacity of the mixture. The flow value exhibited a progressive increase from 2.39 mm at 4.5% binder to 2.78 mm at 6.0%, indicating increased deformation with increasing binder content. Bulk density increased from 2.340 g/cc at 4.5% binder to a maximum of 2.382 g/cc at 5.5%, followed by a decrease to 2.345 g/cc at 6.0%. In contrast, air voids decreased consistently from 5.28% to 3.42% as the binder content increased, reflecting progressive filling of the void spaces by bitumen. The VMA showed a relatively gradual increase from 14.29% to 15.25%, while VFB increased substantially from 59.71% to 82.56%. Considering the combined Marshall stability and volumetric characteristics, 5.5% was selected as the optimum binder content for the conventional DBM. At this binder content, the mixture achieved a maximum Marshall stability of 1255 kg and maximum bulk density of 2.382 g/cc, while maintaining satisfactory flow and void characteristics. Thus, the conventional DBM established a suitable reference mixture for assessing the effectiveness of LDPE modification. The identified optimum binder content and corresponding Marshall characteristics provide an essential baseline for quantifying the subsequent changes produced by incorporation of waste LDPE and for determining the optimum modifier dosage in the modified DBM.

References

1. Gürü M, Çubuk M, Arslan D, Faruk Çubuk M, Özcan İ. Use of waste high density polyethylene as bitumen modifier in asphalt concrete mix. *Materials & Design*. 2004;25(5):441–446.
2. Hassani A, Ganjidoust H, Maghanaki AA. Use of plastic waste in asphalt concrete mixture. *Construction and Building Materials*. 2005;19(8):1–7.
3. Awwad MT, Shbeeb L. The use of polyethylene in hot asphalt mixtures. *American Journal of Applied Sciences*. 2007;4(6):390–396.
4. Al-Hadidy AI, Yi-qiu T. Mechanistic approach for polypropylene-modified flexible pavements. *Construction and Building Materials*. 2009;23(9):2944–

- 2950.
5. Ahmadinia E, Zargar M, Karim MR, Abdelaziz M, Shafigh P. Using waste plastic bottles as additive for stone mastic asphalt. *Materials & Design*. 2011;32(10):4844–4849.
6. Kumar P, Mehndiratta HC, Singh S. Effect of waste polymer modifier on the properties of bituminous concrete mixes. *Construction and Building Materials*. 2011;25(7):2909–2914.
7. Vasudevan R, Sekar ARC, Sundarakannan B, Velkennedy R. A technique to dispose waste plastics in an ecofriendly way—Application in construction of flexible pavements. *Construction and Building Materials*. 2012;28(1):311–320.
8. Ahmadinia E, Zargar M, Karim MR, Abdelaziz M, Shafigh P. Performance evaluation of utilization of waste polyethylene terephthalate (PET) in stone mastic asphalt. *Construction and Building Materials*. 2012;36:984–989.
9. Almeida-Costa A, Benta A. Economic and environmental impact study of warm mix asphalt with recycled concrete aggregates and waste polyethylene. *Construction and Building Materials*. 2016;111:36–45.
10. Giri JP, Panda M, Sahoo UC. Use of waste polyethylene for modification of bituminous paving mixes containing recycled concrete aggregates. *Road Materials and Pavement Design*. 2019;20(6):1445–1461.
11. Wu S, Montalvo L. Repurposing waste plastics into cleaner asphalt pavement materials: A critical literature review. *Journal of Cleaner Production*. 2021;280:124355.
12. Ma Y, Wang S, Chen Y, et al. The utilization of waste plastics in asphalt pavements: A review. *Construction and Building Materials*. 2021;280:122592.
13. Rahman MT, Mohajerani A, Giustozzi F. The use of plastic waste in asphalt: A critical review on asphalt mix design and Marshall properties. *Construction and Building Materials*. 2021;309:125185.
14. *Investigation and optimization of waste LDPE plastic as a modifier of asphalt mix for highway asphalt: Case of Ethiopian roads*. *Construction and Building Materials*. 2021.
15. Moghaddam TB, Soltani M, Karim MR. Using waste plastics as asphalt modifier: A review. *Materials*. 2022;15(1):110.
16. *A review on the utilization of waste material in asphalt pavements*. *Materials Today: Proceedings*. 2022.
17. *Structural Performance of Waste Plastic Bottles Modified Asphalt: A Review*. *Resources*. 2023;12(1):10.
18. Li H, Han Y, Guangxun E, Sun Y, Liu X, Ren J, Lin Z. Recycling of waste polyethylene in asphalt and its performance enhancement methods: A critical literature review. *Journal of Cleaner Production*. 2024;451:142072.
19. Khan I, et al. Exploring the potential of waste plastic-modified asphalt: A systematic review of blending ratios, mixing conditions, and rheological properties. *Construction and Building Materials*. 2024.
20. *Plastic -Waste-Modified Asphalt for Sustainable Road Infrastructure: A Comprehensive Review*. *Sustainability*. 2025;17(21):9832.